HumiSeal® 1B59LU Synthetic Rubber Conformal Coating

Technical Data Sheet

HumiSeal® 1B59LU is a fast drying, single component, synthetic rubber conformal coating that contains methylcyclohexane solvent that is more environmentally friendly than traditional solvents. Because of its unique base polymer, HumiSeal® 1B59LU has low moisture vapor permeability. The coating demonstrates excellent heat resistance and flexibility, low stress on components, fluoresces under UV light for ease of inspection and is easily repaired.

Representative Properties of HumiSeal® 1B59LU

Density, per ASTM D1475	0.795±0.015 g/ml @23℃
Solids Content, per ASTM D1644	18.5±1.5 %
Viscosity, per ASTM D1084	210±70 mPa/s @23℃
VOC	648 grams/liter
Drying Time to Handle	10 minutes
Recommended Coating Thickness	25 – 75 microns
Recommended Curing Conditions	24hrs @RT or 30 min @70℃
Recommended Thinner	HumiSeal® Thinner 904
Recommended Stripper	HumiSeal® Thinner 904
Shelf Life at Room Temperature, DOM	12 months
Continuous Use Temperature	-40℃ to 150℃
Young's Modulus	20 MPa @23℃
Dielectric Withstand Voltage, per MIL-I-46058C	>1500 volts
Dielectric Constant at 1MHz and 25℃ per ASTM D-150-98	1.9
Dissipation Factor at 1MHz and 25℃ per ASTM D-150-98	0.004
Insulation Resistance, per MIL-I-46058C	8.5×10^{15} ohms

Application of HumiSeal® 1B59LU

Cleanliness of the substrate is of extreme importance for the successful application of a conformal coating. Surfaces must be free of moisture, dirt, wax, grease, flux residues and all other contaminations. Contamination under the coating could cause problems that may lead to assembly failures. If this product will be applied over “no clean” assembly materials, the user should conduct adequate testing to verify compatibility and reliability of the coated assembly.

Dipping

Depending on the complexity, density and configuration of components on the assembly, it may be necessary to reduce the viscosity of HumiSeal® 1B59LU with HumiSeal® Thinner904 in order to obtain a uniform film. Once optimum viscosity is determined, a controlled rate of immersion and withdrawal (5–15 cm/min) will further ensure even deposition of the coating and a uniform film. During the application, evaporation of solvent causes an increase in viscosity that should be adjusted by adding small amounts of HumiSeal® Thinner904. Viscosity in the dip tank should be checked regularly using a simple measuring device such as a Zahn or Ford viscosity cup.

Spraying

HumiSeal® 1B59LU can be sprayed using conventional spraying equipment. Spraying should be done in an environment with adequate ventilation so that the vapor and mist are carried away from the operator. The addition of HumiSeal® Thinner904 is necessary to ensure a uniform spray pattern resulting in pinhole-free film. The amount of thinner and spray pressure will depend on the specific type of spray equipment used and operator technique. The recommended ratio of HumiSeal® 1B59LU to HumiSeal® Thinner904 is 1:3 by volume; however the ratio may need to be adjusted to obtain a uniform coating.

Brushing

HumiSeal® 1B59LU may be brushed with a small addition of HumiSeal® Thinner904. Uniformity of the film depends on component density and operator technique.

Storage

HumiSeal® 1B59LU should be stored away from excessive heat or cold, in tightly closed containers. HumiSeal® products may be stored at temperatures of 5 to 40℃. Prior to use, allow the product to equilibrate for 24 hours at a room temperature of 18 to 32℃.

Caution

Application of HumiSeal® Conformal Coatings should be carried out in accordance with local safety regulations.

The solvents in HumiSeal® Conformal Coatings are flammable. Material should not be used in presence of open flame or sparks. Use only in well-ventilated areas to avoid inhalation of vapors or spray. Avoid contact with skin and eyes.

Consult MSDS/SDS prior to use.

*The information contained here is provided for product selection purposes only and is not to be considered specification or performance data. Under no circumstance will the seller be liable for any loss, damage, expense or incidental or consequential damage of any kind of arising in connection with the use or inability to use its product.