

HumiSeal® 1B18 Aerosol Conformal Coating Technical Data Sheet

HumiSeal® 1B18 Aerosol is a fast drying, clear acrylic conformal coating, intended for use on printed circuit assemblies. The product is conveniently dispensed from aerosol cans utilizing an environmentally safe, non-ODP propellant, and contains UV tracer for inspection under black light. The coating may be removed chemically using HumiSeal® Stripper 1080. HumiSeal® 1B18 Aerosol is RoHS Directive 2002/95/EC compliant and recognized under UL File Number E105698.

Properties of HumiSeal® 1B18 Aerosol

Solids Content, % by weight per Fed-Std-141, Meth. 4044	7 ± 1 %
VOC	687.5 grams/litre
Drying Time to Handle per Fed-Std-141, Meth. 4061	30 minutes
Recommended Coating Thickness	25 - 75 microns
Recommended Curing Conditions	24 hrs @ RT or 2 hrs @ 76°C
Time Required to Reach Optimum Properties	7 days
Recommended Stripper	HumiSeal® Stripper 1080, 1080EU
Shelf Life at Room Temperature, DOM	24 months
Thermal Shock, 50 cycles per MIL-I-46058C	-65°C to 125°C
Coefficient of Thermal Expansion - TMA	67 ppm/°C
Glass Transition Temperature - DSC	42°C
Modulus - DMA	11.1 MPa
Dielectric Withstand Voltage, per MIL-I-46058C	>1500 volts
Dielectric Breakdown Voltage, per ASTM D149	6300 volts
Dielectric Constant, at 1MHz and 25°C, per ASTM D150-98	2.6
Dissipation Factor, at 1MHz and 25°C, per ASTM D150-98	0.010
Insulation Resistance, per MIL-I-46058C	5.5×10^{14} ohms (550TΩ)
Moisture Insulation Resistance, per MIL-I-46058C	7.0×10^{10} ohms (70GΩ)
Fungus Resistance, per ASTM G21	Passes

Application of HumiSeal® 1B18 Aerosol

1. Allow 48 hours minimum to reach room temperature before using cans stored or received during cold weather.
2. When applied in conditions of high ambient humidity, blushing (cloudy white film) may appear. Heating the coated assembly in an oven for 1/2 hour at 76°C eliminates this condition.
3. Cleanliness of the substrate is extremely important to the successful application of a conformal coating. Surfaces should be free of moisture, dirt, wax, grease and all other contaminants. Otherwise, ionic or organic residues on the substrate could be trapped under the coating and cause problems with adhesion or electrical properties. The highest long term reliability for a coated printed circuit assembly will be when the conformal coating is applied over a clean, dry substrate.

   The application of conformal coatings over no clean flux is a common practice. The user should perform adequate testing to confirm compatibility between the conformal coating and their particular assembly materials and process conditions. Please contact HumiSeal for additional information.

HumiSeal® 1B18 Aerosol Technical Data Sheet

4. Mask areas not requiring coating from overspray using suitable non-silicone masking methods or materials.
5. Shake can vigorously before using and repeat frequently during use.
6. Best results are obtained by spraying from a distance of 30 - 40cm in light even coats. A film thickness of 25 - 75 microns is sufficient to provide protection.
7. To clean nozzle after use, hold can upside down, then press nozzle for a few seconds.

Caution
Application of HumiSeal® Conformal Coatings should be carried out in accordance with local and National Health and Safety regulations.

The solvents in HumiSeal® Conformal Coatings are flammable. Material should not be used in presence of open flame or sparks. Use only in well-ventilated areas to avoid inhalation of vapours or spray. Avoid contact with skin and eyes.

Consult MSDS/SDS prior to use.

Contact HumiSeal®

HumiSeal North America
201 Zeta Drive
Pittsburgh, PA 15238
USA
Tel: +1 412-828-1500
Toll Free (US only): 866-828-5470
sales@humiseal.com

HumiSeal Technical Center
295 University Avenue
Westwood, MA 02090
USA
Tel: +1 781-332-0734
Fax: +1 781-332-0703
techsupport@humiseal.com

HumiSeal Europe
Albany Park, Frimley Road
Camberley, Surrey GU16 7PH
UK
Tel: +44 (0)1276 691100
Fax: +44 (0)1276 691227
europeansales@chasecorp.com

HumiSeal Europe Support
Tel: +44 (0)1276 691100
Fax: +44 (0)1276 691227
europetechsupport@chasecorp.com

HumiSeal S.A.R.L
4/6 Avenue Eiffel
78420 Carrieres-Sur-Seine
France
Tel: +33 (0) 1 30 09 86 86
Fax: +33 (0) 1 30 09 86 87
humiseal.sarl@chasecorp.com

HumiSeal Asian Support
Tel: 852-9451-6434
Fax: 852-2413-6289
asiatechsupport@humiseal.com

The information contained here is provided for product selection purposes only and is not to be considered specification or performance data. Under no circumstance will the seller be liable for any loss, damage, expense or incidental or consequential damage of any kind arising in connection with the use or inability to use its product. Specific conditions of sale and Chase's limited warranty are set out in detail in Chase Corporation Terms and Conditions of Sale. Those Terms and Conditions are the only source that contain Chase's limited warranty and other terms and conditions.